

<b>Rockwell Hardness HRC</b>	<b>Brinell Hardness HB</b>	<b>Vickers Hardness HV</b>	<b>Tensile Strength MPa</b>
25	253	266	854
30	287	302	970
35	329	345	1111
40	373	392	1262
45	424	446	1442
50	488	513	1668
55	566	596	1979
60		698	